

AF-200

Dielectric industrial grease

Description

The AF-200 is a superior quality industrial multi-purpose grease with ANTIFRICTION TREATMENT which outperforms lithium, aluminum and polyurea base standard greases of the same viscosity.

Characteristics and Benefits

The AF-200 unique formulation includes such elements as:

- Overbased calcium sulfonate complex;
- Superior quality mineral base oil;
- PROLAB's ANTIFRICTION TREATMENT.

Its exclusive PROLAB formula brings the AF-200 industrial multi-purpose grease to an exceptional level of performance: it reduces friction, protects against rust, corrosion and oxidation, provides exceptional load resistance as well as excellent mechanical stability and moisture resistance.

The exceptional properties of the AF-200 industrial multi-purpose grease bring notable benefits from regular use including less frequent lubricating jobs and substantial savings on maintenance costs. Available in NLGI grade 2.

Types of Application

The AF-200 is a must for every type of business, no matter what the size or the nature of the operations. It performs best in the most demanding conditions, such as in bearings with high loads and an average rotational speed of more or less 1750 rpm, as well as joints, pins, runners and journal bearings lubrication. Dielectric up to 7 KV.

Directions for Use

Always use AF-200 industrial multi-purpose grease in reference to the equipment manufacturer's manual.

Warning

Whenever performing a grease change, make sure to validate the compatibility of the various greases used (refer to [PROLAB's grease compatibility chart](#)).

Available Sizes

435 g, 17 kg, 55 kg, 180 kg

Product Code

#283

Characteristics	ASTM Test	Typical Values
Appearance		Brown
N.L.G.I. Grade		2
Viscosity at 40°C	D445	230 cSt
Viscosity at 100°C	D445	21 cSt
Viscosity Index	D2270	108
Dropping Point	D2265	300°C
Oil Separation at 25°C	D1742	0,2%
Consistency 60 X	D217	280 (1/10mm)
Shear Stability 100,000 X	D217	2,3%
Shear Stability 10,000 X (50/50 with water)	D217	7,5%
Roll Stability	D1831	3,9%
Bearing Leak Tendency	D4290	4 g
Oxydation Resistance 1000h	D942	9 psi
Bearing Life	D3527	100 hrs
4-ball Wear (75°C, 40 kg, 1200 t/m, 1h)	D2266	0,38 mm
Load Wear Index	D2596	100
Weld Load	D2596	620 kg
Timken OK Load	D2509	32 kg

Rust Preventative	D1743	Pass
Water spray resistance at 79°C	D1264	2,0%
Corrosion - Copper Strip	D130	1b
Dielectric Breakdown	D877	7 Kv
Salt Fog Corrosion (1 mil d.f.t.)	B117	>300 hrs.
Oil Separation (100°C, 30 hrs.)	D6184	n/a
Pumpability		
23°C (73°F)		456 g/min
-18°C (0°F)		7 gr/min
-23°C (-10°F)		2 gr/min
-29°C (-20°F)		0 gr/min
-34°C (-30°F)		0 gr/min

ENSURE YOU HAVE THE MOST UP-TO-DATE INFORMATION BY REGULARLY VISITING THE PRODUCT PAGE ON OUR WEBSITE TO ACCESS THE LATEST VERSION OF THIS TECHNICAL DATA SHEET.

©Prolab - Aug 2023